



Ultra HTS OR

High-solids urethane protective topcoat

- 91% solids, aliphatic urethane (solvent-based)
- VOC = 2 grams / liter
- Low odor & non-yellowing
- Extreme chemical resistance & no tire staining
- Requires grinding preparation
- Not recommended for existing polished concrete
- Prime with UltraSpartic or MC-UV Epoxy
- 20+ minute working time/wet edge. 75 minute pot-life
- Add UltraColor Pigment Pack for opaque coloring
- High-gloss or semi-gloss (with Part C)
- Hardness = 5H-6H. 1000 cycle taber abrasion = 17mg loss
- 8 hour dry time
- Dries slower in low humidity (apply between 20-90% RH)
- **Recoat Window:** 24 Hours
- **Coverage:** Primer @ 600-800 SF/gal. Ultra HTS @ 500 SF/gal.

IMPACT

Water-based urethane protective topcoat



- 50% solids, aliphatic urethane (water-based)
- VOC = 95 grams / liter
- Very low odor & non-yellowing
- Great chemical-resistance, potential tire staining
- Does not require grinding preparation
- May be applied to existing polished and hard troweled concrete
- Apply direct-to-concrete *(may need 2 coats for rough or porous concrete)*
- 3-5 minute working time/wet edge. 45-90 minute pot-life *(4hr vs. 8hr)*
- Clear formulation only
- High-gloss or matte sheens available. Semi-gloss achieved with Ultra Grip or UDT Aggregate added
- Hardness = 2H. 1000 cycle taber abrasion = 45 mg loss
- 4 hour or 8 hour dry times available
- Dries faster in low humidity (apply at 70% RH or below)
- **Recoat Window:** 4 Hr: 3-5 Hrs. 8 Hr: 6-10 Hrs.
- **Coverage:** 600-800 SF/gal. (thin coat) 300-400 SF/gal. (thick coat)

